

Diamond Vogel 

EVERCryl



EXTERIOR 100% ACRYLIC LATEX

The foundation of quick and successful exterior painting projects

Diamond Vogel

AN EFFICIENT SOLUTION WITH GREAT LOOKING RESULTS

EverCryl Exterior 100% Acrylic Latex Finish meets the demands of discerning painting contractors and homeowners with its long lasting acrylic formula providing great looking results, the ability to be used at low temperatures, and easy application by brush, roll, or spray. EverCryl resists fading so your colors remain vibrant and is highly flexible guarding against cracking and peeling ensuring your project will continue to look great for years. EverCryl can be used on new or previously painted residential and commercial projects and is ideal for siding, gutters, soffits and foundations.



PHYSICAL PROPERTIES	FLAT	SATIN
Finish	0-5 @ 85°	30-35 @ 85°
Resin Type	100% Acrylic	
Dry Time to Touch	30 to 120 minutes at greater than 50°F and 50% Relative Humidity 2 to 4 hours at 35°F to 49°F 50% Relative Humidity	
Dry Time to Recoat	2 to 4 hours at greater than 50°F and 50% Relative Humidity 24 hours at 35°F to 49°F and 50% Relative Humidity	
Recommended Dry Film Thickness per coat	2.0 to 3.0 mils	
Practical Coverage at Recommended DFT	176 to 265 ft ² /gallon	155 to 233 ft ² /gallon
Solids by Volume	33%	29%
VOC	<50 g/L	<50 g/L



OUR FAMILIES' COMMITMENT TO YOU

Our founder, Andrew Vogel decided that the only paint good enough for the barns and homes in the varied and often harsh Midwest climate was paint he perfected himself. So in 1926, from a modest "workshop laboratory," a paint company was born. Four generations, seven manufacturing facilities,

70 service centers, and millions of gallons of paint later, we are still as stubborn. We still insist on perfecting our own formulas, producing and distributing our own products, and servicing our customers with the kind of passion and commitment worthy of Andrew's name.



Diamond Vogel
T/800-72-VOGEL F/712-737-4998
1110 Albany Place SE Orange City, IA 51041
www.diamondvogel.com

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products.